Item No.: JM7480-1


TECHNICAL DATA SHEET



ARTICLE: AQUA-SUN-PROTECT

ITEM-NO.: JM7480-1

SYSTEM: Water-Based, 1C Multi-Layer Coating



PRODUCT PROPERTIES

Aqua-Sun-Protect JM7480-1 is a transparent, water-based, 1C multi-layer coating and is characterised by:

- very high light stability
- very pleasant touch
- easy to process
- fast drying
- good blocking resistance

SCOPE OF APPLICATION

Suitable for coating of:

- several solid timbers (Except tropical and ingredient rich woods)
- Decorative surfaces that are exposed to strong sunlight

The product is well suited for the application on:

wooden composites and components

TECHNICAL DATA		APPLICATION			
• Colour:	clear Can be coloured with pigments, transparent to opaque (wood structure is preserved)	→ 1/2 → 1/2 → 1/2			
		Application quantity per layer (g/m²)			90-120
Gloss level:	natural effect	Quantity of applied layers Jet nozzle (mm)			1-2
	< 3 GU 60° (on treated board depending on substrate and sanding)				
Viscosity:	48-56 s DIN 53211/ 4 mm	Air pressure (bar)			
Density:	approx. 1,0198 g/cm ³	Material pressure (bar)			
DRYING		HARDENER, THINNER, RETARDER			
Dust-dry after	15 min		Hardener	-	
Sandable after	1 h				
Overcoatable after	1 h				
Stackable after	24 h				
Completely dried after		\$	Thinner	If necessary: water	
Cured after		Ä			
(at 20 °C and 35-65 % relative humidity and depending on the applied quantity)			Retarder	-	

TECHNICAL DATA SHEET



STORAGE



Store material in a tightly closed container and under dry and cool conditions. Protect from frost.

d....

CLEANING

Clean tools immediately after use with

Water

Shelf life:

JM7480-1:

12 months

(when stored in the original unopened containers)

SPECIAL GUIDANCE

- Stir well before using!
- The substrates which should be coated have to be conditioned 12 hours before coating.
- It is recommended to perform preliminary trials to test the suitability of the coating system with the desired substrate.
- The surfaces have to be perfectly sanded, dry, free of grease, oil and silicones before the application.
- High humidity and a moisture content above 10% must be avoided at all costs. High humidity leads to longer drying times. The indicated times depend on the application quantity, the room temperature and the relative humidity.
- Protect the containers from drying out and always close them tightly immediately after removing the material.
- Avoid contact with iron, copper, zinc an aluminium. Use equipment made of rustproof materials only.
- Thinners or solvents of conventional lacquers must not get into the water-based lacquer.
- When opening the container, do not allow any encrusted lacquer residues to fall into the lacquer. These do not dissolve and can only be removed by sieving. Do not allow lacquer residues to enter the sewer system, but dry out and dispose of with industrial waste.
- When changing from water-based lacquer to solvent-based lacquers, thoroughly rinse spray equipment with diluted Water-based Lacquer Cleaning Concentrate AC 460, then with water, then with Uni Washing Solvent V 803 or DD Thinner V 2244. When changing to water-based lacquers again, clean in reverse order.
- AQUA-SUN-PROTECT is ideally suited for weatherprotected wall and ceiling coverings.
- Due to ist excellent light stability, AQUA-SUN-PROTECT protects the wood against natural yellowing and is suitable as decorative wood protection.

TESTING STANDARDS

Free of formaldehydes

Safety guidance:

The information in this technical data sheet is based on the current knowledge and experience of PLANTAG Coatings GmbH. The product processor is not exempted from its own testing and testing of the products with regard to the intended use as well as the wealth of possible influences during processing and application. Existing laws and regulations are to be observed by the recipient of our products in their own responsibility. Labeling in accordance with the Ordinance on Hazardous Substances and Transport Law can be found in the safety data sheet. A legally binding assurance of certain properties or suitability for a specific purpose cannot be derived from our information. Recommendations deviating from the information in our technical data sheets are only binding for us if they have been confirmed in writing. Our terms and conditions are an integral part of this technical information sheet [Jan-24]

PLANTAG Coatings GmbH Plantagenweg 34-38 32758 Detmold GERMANY

Fon: +49 5231 6002 66° Fax: +49 5231 6002 966° F-Mail: info@iordanlacke.c

JORDAN LACKE – a brand of PLANTAG Coatings GmbH