

ARTICLE: 1C CLASSIC-FINISH
ITEM-NO.: CF 52X
SYSTEM: Water-Based, 1C Parquet Lacquer



PRODUCT PROPERTIES

JORDAN PARQUETLINE lacquers and oils are perfectly suitable for professional parquet floorings. They provide protection and long-term preservation of the value for the surfaces.

1C CLASSIC-FINISH CF 52X is a clear, water-based, 1C parquet lacquer which is suitable for the surface treatment of parquet flooring in private areas, due to its good abrasion and wear resistance.

CF 52X is characterised by:

- good leveling properties
- easy-to-use
- good resistance against common household chemicals
- no hazardous substances

SCOPE OF APPLICATION

Suitable for coatings of:

- several solid timbers (Except tropical and ingredient rich woods)
- veneered substrates


The product is well suited for the application on:

- parquet flooring

TECHNICAL DATA

- Colour: transparent
- Gloss level: matt (CF 525)
semi-matt (CF 523)
- Viscosity: 20-25 s DIN 53211/ 4 mm
- Density: approx. 1,02 g/cm³



APPLICATION



Application quantity (g/m ²)	100-120
Quantity of applied layers	min. 2
Jet nozzle (mm)	
Air pressure (bar)	
Material pressure (bar)	

DRYING

HARDENER, THINNER, RETARDER

Dust-dry after	1-2 h		Hardener	-
Sandable after	12 h			
Overcoatable after	2 h			
Stackable after				
Completely dried after	24 h		Thinner	If necessary: water add max.: 5 %
Cured after	7 d			
(at 20 °C and 35-65 % relative humidity and depending on the applied quantity)			Retarder	-

Item No.: CF 52X

STORAGE



Store material in a tightly closed container and under dry and cool conditions.

Shelf life:

CF 52X: 6 months

(when stored in the original unopened containers)

CLEANING



Clean tools immediately after use with

- Water

SPECIAL GUIDANCE

- Stir well before using!
- The substrates which should be varnished have to be conditioned 12 hours before varnishing.
- It is recommended to perform preliminary trials to test the suitability of the coating system with the desired substrate.
- The surfaces have to be perfectly sanded, dry, free of grease, oil and silicones before the application.
- Protect the containers from drying out and always close them tightly immediately after removing the material.
- Avoid contact with iron, copper, zinc and aluminium. Use equipment made of rustproof materials only.
- Thinners or solvents of conventional lacquers must not get into the water-based lacquer.
- When opening the container, do not allow any encrusted lacquer residues to fall into the lacquer. These do not dissolve and can only be removed by sieving. Do not allow lacquer residues to enter the sewer system, but dry out and dispose of with industrial waste.
- The lacquer is not suitable for the coating of vertical surfaces.

TESTING STANDARDS

Tested according to:

- EN 71, part 3 free of extractable heavy metals
- DIN ISO 2409 GT 0 adhesion

Additional tests:

- DIBt approval (in progress)
- GISCODE: W2 +
- decopaintcompliant
- developed according to REACH

Safety guidance:

The information in this technical data sheet is based on the current knowledge and experience of PLANTAG Coatings GmbH. The product processor is not exempted from its own testing and testing of the products with regard to the intended use as well as the wealth of possible influences during processing and application. Existing laws and regulations are to be observed by the recipient of our products in their own responsibility. Labeling in accordance with the Ordinance on Hazardous Substances and Transport Law can be found in the safety data sheet. A legally binding assurance of certain properties or suitability for a specific purpose cannot be derived from our information. Recommendations deviating from the information in our technical data sheets are only binding for us if they have been confirmed in writing. Our terms and conditions are an integral part of this technical information sheet [Jan-21]

PLANTAG Coatings GmbH

Plantagenweg 34-38
32758 Detmold

GERMANY

Fon: +49 5231 6002 661
Fax: +49 5231 6002 9661
E-Mail: info@plantag.de

PLANTAG COATINGS – Competence in lacquer