


ARTICLE: JOCOPHEN-BASE COAT
ITEM-NO.: H 2010
SYSTEM: Solvent-Based, 2c Sealer



PRODUCT PROPERTIES

JORDAN CLASSICLINE are reliable solvent-based lacquer systems, which are particularly fast-drying and economical.

JOCOPHEN-BASE COAT H 2010 is a clear, solvent-based, 2C sealer and is easy to use thanks to its uncomplicated handling and fast drying. Besides that the basecoat has an excellent dry sandability.

H 2010 is characterised by:

- very good insulating effect

SCOPE OF APPLICATION

Suitable for coatings of:

- several solid timbers
- veneered substrates
- ingredient-rich and exotic woods



The product is well suited for the application on:

- furniture surfaces

TECHNICAL DATA

- Colour: transparent
- Gloss level: glossy
- Viscosity: 27-30 s DIN 53211/ 4 mm
- Density: approx. 0,918 g/cm³




APPLICATION





Application quantity (g/m ²)	140-160	
Quantity of applied layers	1-3	
Jet nozzle (mm)	1,5-1,8	0,28-0,33
Air pressure (bar)	2,5-3,5	1,0-2,0
Material pressure (bar)	100-120	

DRYING

HARDENER, THINNER, RETARDER

Dust-dry after	30 min		Hardener	2:1 by volume with hardener H 2242
Sandable after	4-6 h		Pot life	with hardener H 2242: 7 h (shortens at high temperatures)
Overcoatable after	6-8 h		Thinner	If necessary: V2244
Stackable after	15 h		Retarder	If necessary: V 19 add max.: 5 %
Completely dried after	15 h			
Cured after	7 d			
(at 20 °C and 35-65 % relative humidity and depending on the applied quantity)				

Item No.: H 2010

STORAGE	CLEANING
 <p>Store material in a tightly closed container and under dry and cool conditions.</p> <p>Shelf life:</p> <p>H 2010: 12 months</p> <p>Hardener H 2242: 6 months</p> <p>(when stored in the original unopened containers)</p>	 <p>Clean tools immediately after use with</p> <ul style="list-style-type: none"> ▪ Nitro-Thinner V 1415 or ▪ DD-Thinner V 2244 or ▪ UNI-WASHING SOLVENT 803
SPECIAL GUIDANCE	TESTING STANDARDS
<ul style="list-style-type: none"> ▪ Stir well before using! ▪ The substrates which should be varnished have to be conditioned 12 hours before varnishing. ▪ It is recommended to perform preliminary trials to test the suitability of the coating system with the desired substrate. ▪ The surfaces have to be perfectly sanded, dry, free of grease, oil and silicones before the application. ▪ Protect the containers from drying out and always close them tightly immediately after removing the material. ▪ Solvent-based products are flammable, also during processing and drying. ▪ JOCOPHEN-BASE COAT is not suitable for bleached wood. ▪ JOCOPHEN-BASE COAT can be painted with JOCOPHEN DD varnishes 2243-H 2246, as well as with GIESS-COLORLUX H 371-376. 	<p>Tested according to:</p> <ul style="list-style-type: none"> ▪ EN 71, part 3 free of extractable heavy metals

Safety guidance:

The information in this technical data sheet is based on the current knowledge and experience of PLANTAG Coatings GmbH. The product processor is not exempted from its own testing and testing of the products with regard to the intended use as well as the wealth of possible influences during processing and application. Existing laws and regulations are to be observed by the recipient of our products in their own responsibility. Labeling in accordance with the Ordinance on Hazardous Substances and Transport Law can be found in the safety data sheet. A legally binding assurance of certain properties or suitability for a specific purpose cannot be derived from our information. Recommendations deviating from the information in our technical data sheets are only binding for us if they have been confirmed in writing. Our terms and conditions are an integral part of this technical information sheet [Feb-21]

PLANTAG Coatings GmbH
 Plantagenweg 34-38
 32758 Detmold
 GERMANY
 Fon: +49 5231 6002 661
 Fax: +49 5231 6002 9661
 E-Mail: info@plantag.de
PLANTAG COATINGS – Competence in laquer