

**ARTICLE:** ECO-BASE  
**ITEM-NO.:** JB7500-0  
**SYSTEM:** Water-Based, 1C Sealer



### PRODUCT PROPERTIES

Eco-Base JB7500-0 is a water-based, 1C sealer and is characterised by:

- good accentuation the wood surface
- high resistance to creams and perspiration
- no hazardous substances
- very good leveling properties

### SCOPE OF APPLICATION

Suitable for coating of:

- several solid timbers (Except tropical and ingredient rich woods)

The product is well suited for the application on:

- parquet flooring

### TECHNICAL DATA

- Colour: transparent
- Gloss level: -
- Viscosity: 25-30 s DIN 53211/ 4 mm
- Density: approx. 1,03 g/cm<sup>3</sup>



### APPLICATION



Application quantity per layer (g/m <sup>2</sup> )	80-120	
Quantity of applied layers	1	
Jet nozzle (mm)	1,8-2	0,28-0,33
Air pressure (bar)	3-4	1-2
Material pressure (bar)		100-120

### DRYING

### HARDENER, THINNER, RETARDER

Dust-dry after	0,5 h		Hardener	-
Sandable after	2 h			
Overcoatable after	2 h			
Stackable after				
Completely dried after	12-24 h		Thinner	If necessary: water add max.: 5 %
Cured after	7 d			
( at 20 °C and 35-65 % relative humidity and depending on the applied quantity)			Retarder	-

Item No.: JB7500-0

## STORAGE



Store material in a tightly closed container and under dry and cool conditions. Protect from frost.

### Shelf life:

JB7500-0: 12 months

(when stored in the original unopened containers)

## CLEANING



Clean tools immediately after use with

- Water

## SPECIAL GUIDANCE

- Stir well before using!
- The substrates which should be coated have to be conditioned 12 hours before coating.
- It is recommended to perform preliminary trials to test the suitability of the coating system with the desired substrate.
- The surfaces have to be perfectly sanded, dry, free of grease, oil and silicones before the application.
- High humidity and a moisture content above 10% must be avoided at all costs. High humidity leads to longer drying times. The indicated times depend on the application quantity, the room temperature and the relative humidity.
- Protect the containers from drying out and always close them tightly immediately after removing the material.
- Avoid contact with iron, copper, zinc and aluminium. Use equipment made of rustproof materials only.
- Thinners or solvents of conventional lacquers must not get into the water-based lacquer.
- When opening the container, do not allow any encrusted lacquer residues to fall into the lacquer. These do not dissolve and can only be removed by sieving. Do not allow lacquer residues to enter the sewer system, but dry out and dispose of with industrial waste.
- To be used as base coat in combination with Eco-Finish JF7550-3/-4.
- ECO-BASE JB7500-0 is not suitable for the coating of vertical surfaces.
- Suitable for effectively reducing joint sticking.

## TESTING STANDARDS

- EN 71, part 3 free of extractable heavy metals
- DIN-68861-1B chemical resistance
- DIN ISO 2409 GT 0 adhesion
- GISCODE: W2 +
- decopaintcompliant
- developed according to REACH

### Safety guidance:

The information in this technical data sheet is based on the current knowledge and experience of PLANTAG Coatings GmbH. The product processor is not exempted from its own testing and testing of the products with regard to the intended use as well as the wealth of possible influences during processing and application. Existing laws and regulations are to be observed by the recipient of our products in their own responsibility. Labeling in accordance with the Ordinance on Hazardous Substances and Transport Law can be found in the safety data sheet. A legally binding assurance of certain properties or suitability for a specific purpose cannot be derived from our information. Recommendations deviating from the information in our technical data sheets are only binding for us if they have been confirmed in writing. Our terms and conditions are an integral part of this technical information sheet [Sep-24]

### PLANTAG Coatings GmbH

Plantagenweg 34-38  
32758 Detmold  
GERMANY  
Fon: +49 5231 6002 661  
Fax: +49 5231 6002 9661  
E-Mail: info@jordanlacke.de

JORDAN LACKE – a brand of PLANTAG Coatings GmbH