

ARTICLE: DECO-OIL-NATURAL-WAX
ITEM-NO.: JW1680-3
SYSTEM: Solvent-Based, 1C Oil-Wax-Combination



PRODUCT PROPERTIES

SCOPE OF APPLICATION

Deco-Oil-Natural-Wax JW1680-3 is a transparent, solvent-based, 1C oil-wax-combination and is characterised by:

- good penetration
- good water resistance
- good accentuation the wood surface

Suitable for coating of:

- several solid timbers (Except tropical and ingredient rich woods)
- veneered substrates


The product is well suited for the application on:

- furniture surfaces
- doors
- parquet flooring
- wooden composites and components
- staircase components and steps
- surfaces in kitchen and bathroom areas

TECHNICAL DATA

APPLICATION



- Colour: transparent
- Gloss level: matt
- Viscosity: approx. 20 s DIN 53211/ 4 mm
- Density: approx. 0,889 g/cm³



Application quantity per layer (g/m ²)	10-30
Quantity of applied layers	1-3
Jet nozzle (mm)	
Air pressure (bar)	
Material pressure (bar)	

DRYING

HARDENER, THINNER, RETARDER

Dust-dry after	1 h		Hardener	-
Sandable after	8 h			
Overcoatable after	8 h			
Stackable after				
Completely dried after	24 h		Thinner	-
Cured after	10 d			
(at 20 °C and 35-65 % relative humidity and depending on the applied quantity)			Retarder	-

Item No.: JW1680-3

STORAGE



Store material in a tightly closed container and under dry and cool conditions. Protect from frost.

Shelf life:

JW1680-3: 6 months

(when stored in the original unopened containers)

CLEANING



Clean tools immediately after use with

- Nitro-Thinner V1415 or
- DD-Thinner V2244-0 or
- UNI-WASHING-SOLVENT V803

SPECIAL GUIDANCE

- Stir well before using!
- The substrates which should be coated have to be conditioned 12 hours before coating.
- It is recommended to perform preliminary trials to test the suitability of the coating system with the desired substrate.
- The surfaces have to be perfectly sanded, dry, free of grease, oil and silicones before the application.
- High humidity and a moisture content above 10% must be avoided at all costs. High humidity leads to longer drying times. The indicated times depend on the application quantity, the room temperature and the relative humidity.
- Protect the containers from drying out and always close them tightly immediately after removing the material.
- Solvent-based products are flammable, also during processing and drying.
- **Risk of spontaneous combustion with cloth or paper towels wetted with natural oil or furniture oil products (autoxidation)!**
- **Soaked application cloths should therefore be dried outdoors or stored in a closed, fireproof container. Soiled rags can also be kept covered with water for at least 48 hours, after which they can be disposed of according to local regulations. Keep away from oxygen and light.**
- **Products which dry by oxidation (e.g. oils) and products which form highly flammable residues (e.g. NC paints) must not be applied in the same spraying booth because of the risk of spontaneous combustion. Only use in spraying booths intended for this purpose. Remove spray mist contamination regularly.**
- JW1680-3 is applied in 1-3 working steps with intermediate sanding. Apply oil in excess and allow to react for approx. 5-10 min. To avoid shiny spots, the excess oil must be removed completely afterwards.

TESTING STANDARDS

- DIN EN 71, part 3 free of extractable heavy metals
- DIN 53160 resistant to saliva and perspiration
- DIN-68861-1C chemical resistance
- decopaint-compliant
- free of formaldehyde
- free of cobalt
- free of butanonoxim

Safety guidance:

The information in this technical data sheet is based on the current knowledge and experience of PLANTAG Coatings GmbH. The product processor is not exempted from its own testing and testing of the products with regard to the intended use as well as the wealth of possible influences during processing and application. Existing laws and regulations are to be observed by the recipient of our products in their own responsibility. Labeling in accordance with the Ordinance on Hazardous Substances and Transport Law can be found in the safety data sheet. A legally binding assurance of certain properties or suitability for a specific purpose cannot be derived from our information. Recommendations deviating from the information in our technical data sheets are only binding for us if they have been confirmed in writing. Our terms and conditions are an integral part of this technical information sheet [Jul-24]

PLANTAG Coatings GmbH
 Plantagenweg 34-38
 32758 Detmold
 GERMANY
 Fon: +49 5231 6002 661
 Fax: +49 5231 6002 9661
 E-Mail: info@jordanlacke.de

JORDAN LACKE – a brand of PLANTAG Coatings GmbH