


ARTICLE: GLASS-HARDENER
ITEM-NO.: GH 135
SYSTEM: Glass lacquer hardener

TECHNICAL DATA	STORAGE
<ul style="list-style-type: none"> ▪ Colour: colourless ▪ Gloss Level: not applicable ▪ Viscosity: 18-20 s DIN 53211/4 mm ▪ Density: approx. 1,03 g/cm³ 	<div style="display: flex; align-items: flex-start;"> <div style="flex: 1;">  <p>Shelf life:</p> <p>GH 135: 6 months</p> <p>(when stored in the original unopened containers)</p> </div> <div style="flex: 2; padding-left: 10px;"> <p>Store material in a tightly closed container and under dry and cool conditions.</p> </div> </div>
SPECIAL GUIDANCE	
<ul style="list-style-type: none"> ▪ The hardener must no longer be used if the viscosity has increased noticeably! ▪ Can be used with all 10:1 mixed solvent-based Jordan 2C-lacquers. ▪ The pot lives are according to the H 132 specifications and can be taken from the technical data sheets of the lacquers used. ▪ Important: As the GLASS-HARDENER GH 135 reacts with the humidity of the ambient air, pot life specifications of more than 8 hours must be reduced to a maximum of 8 hours. ▪ For further information on processing, please refer to the technical data sheets of the corresponding lacquer used. 	

Safety guidance:

The information in this technical data sheet is based on the current knowledge and experience of PLANTAG Coatings GmbH. The product processor is not exempted from its own testing and testing of the products with regard to the intended use as well as the wealth of possible influences during processing and application. Existing laws and regulations are to be observed by the recipient of our products in their own responsibility. Labeling in accordance with the Ordinance on Hazardous Substances and Transport Law can be found in the safety data sheet. A legally binding assurance of certain properties or suitability for a specific purpose cannot be derived from our information. Recommendations deviating from the information in our technical data sheets are only binding for us if they have been confirmed in writing. Our terms and conditions are an integral part of this technical information sheet. [Mai-21]

PLANTAG Coatings GmbH
 Plantagenweg 34-38
 32758 Detmold
 DEUTSCHLAND
 Fon: +49 5231 6002 661
 Fax: +49 5231 6002 9661
 E-Mail: info@jordanlacke.de

JORDAN LACKE – a brand of PLANTAG Coatings GmbH